3348 Route 208, Campbell Hall, NY 10916
Phone: 845-496-1600 Fax: 845-496-1398
12960 Commerce Lakes Drive, A14, Fort Myers, FL 33913
42 Day Farm Road, West Stockbridge, MA 01266
1813 State Route 7, Harpursville, NY 13787

Client:	Aden Aggregates	**Project:**	Grasso Quarry QC 2025
Item:	3/8 Stone	**Project No.:**	250005
Source:	Grasso Quarry	**Lab No.:**	25-1368A
Location:	Stockpile	**Specification:**	DOT
Date Sampled:	10/6/2025	**Sampled By:**	Client
Date Tested:	10/20/2025	**Tested By:**	John Brinsfield

Report of Clay Lumps and Friable Particles in Aggregate

Test Method: ASTM C142, AASHTO T112

Size Fraction		% Retained	% Clay Lumps/Friable Particles
37.5mm to 75mm	1-1/2 to 3 inches		
19.0 mm to 37.5 mm	3/4 to 1-1/2 inch		
9.5 mm to 19.0 mm	3/8 to 3/4 inch	30.1	0.00
4.75 mm to 9.5 mm	#4 to 3/8 inch	64.3	0.00
1.18mm to 4.75mm	#16 to #4		

Total weighted percent **0.00**

Test is performed only on sizes with at least 5% retained.

Emily J. Rodriguez

Report Reviewed By:

The simple acceptance/rejection decision rule is utilized to determine in-tolerance and out of tolerance or pass/fail conditions and no measurement of uncertainty is applied in this determination.

This report shall not be reproduced, except in full, without the written permission of Advance Testing Company, Inc.

The results in this report relate only to the items inspected or tested.